

Klüberfluid C-F 2 Ultra

Operational lubricant for open drives



Benefits for your application

- Service lubricant for open drives with splash or circular lubrication
- Suitable for normal to elevated operating temperatures
- Free from heavy metals, solvents, bitumen, and chlorine
- Easy application
- Optimum tooth face protection

Description

Klüberfluid C-F 2 ULTRA is a mineral oil based aluminium stearate saponified service lubricant especially designed for splash or circular lubrication. It contains special graphite as a solid lubricant, is highly resistant to pressure, and contains anti-wear additives as well as corrosion inhibitors. In extreme cases, this lubricant is suitable for mass temperatures up to 200 °C.

Klüberfluid C-F 2 ULTRA is a non-Newtonian fluid free from bitumen, solvents, heavy metals, and chlorine.

In accordance with AGMA 251.02, Klüberfluid C-F 2 ULTRA is classified among the "Special Compounds" (sect. 3.4). The specifications of table 6, "Extreme Pressure Gear Lubricants", are fully satisfied.

Application

Klüberfluid C-F 2 ULTRA is used for splash, paddle wheel or circular lubrication of open gears.

Possible uses are limited neither by component size nor by driving power. The peripheral speed should not exceed 8.5 m/s. Combined gear and bearing lubrication is not allowed. Drives of

this kind are mainly used in rotary kilns, tube mills, and similar machines as are used in the cement, lime, gypsum, mining and chemical industries.

Application notes

Klüberfluid C-F 2 ULTRA can either be filled into the immersion bath so that lubrication is done by direct transfer of the lubricant to the tooth faces or if you have the circular lubrication system Klübermatic PA the lubricant is force-pumped onto the tooth faces.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	Klüberfluid C-F 2 Ultra
Bucket 25 kg	+
Drum 180 kg	+

Product data	Klüberfluid C-F 2 Ultra
Article number	039075
Colour space	black
Texture	homogeneous
Texture	fluid
Density at 20 °C	approx. 1.00 g/cm ³
Worked penetration, acc. to Klein, 25 °C, lower limit value	410 x 0.1 mm
Worked penetration, acc. to Klein, 25 °C, upper limit value	490 x 0.1 mm



Klüberfluid C-F 2 Ultra

Operational lubricant for open drives

Product data	Klüberfluid C-F 2 Ultra
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 40 °C	approx. 3 200 mm ² /s
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 100 °C	approx. 95 mm ² /s
Application by immersion bath	approx. 5 - 100 °C
Application in circulation lubrication systems	approx. 15 - 80 °C
Functional lubricant film	approx. - 30 °C
Thermal stability of the lubricating film	approx. 200 °C
FZG scuffing test, based on DIN ISO 14635, A/2.76/50, change in weight	approx. 0.2 mg/kWh
FZG scuffing test, based on DIN ISO 14635, A/2.76/50, scuffing load stage	> 12
Four-ball tester, welding load, DIN 51350 pt. 04	>= 7 500 N
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	24 months

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 80 years.

**Klüber Lubrication München SE & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.**

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München SE & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München SE & Co. KG and if source is indicated and voucher copy is forwarded.