

Klüber TP 39 N A-B

Two-component PTFE bonded coating for metal components



Benefits for your application

- **Long component life expectancy**
 - for a wide service temperature range
 - especially in combination with oils or greases
 - due to a highly flexible bonded coating
 - coatings of up to 70 µm thickness can be applied
- **Better component performance**
 - due to less stick-slip
 - due to very high wear resistance
 - as lifetime lubrication is possible

Description

Klüber TP 39 N A/B is a thermosetting, black-coloured high-performance bonded coating made up of two component parts. It has an organic binder containing PTFE as the solid lubricant.

Klüber TP 39 N A/B reduces friction and wear on metal/metal and metal/plastic material pairings. This bonded coating can be used for high mechano-dynamic loads as well as with high temperatures.

Klüber TP 39 N A/B is supplied in liquid form and with a viscosity ready to use. It contains an inflammable solvent mixture (former hazard class A II).

Once applied and hardened, the bonded coating forms a dry lubricating layer with a wide service temperature range, low friction coefficients and a high resistance to wear. Its resistance to chemicals and anticorrosive effect are good.

Klüber TP 39 N A/B excels due to its extraordinarily high wear resistance plus good adhesion on steel and aluminium substrates.

Application

Klüber TP 39 N A/B is used as a dry lubricant for components that require a low friction coefficient but where contamination by oil or grease is highly undesirable. Typical applications are found, for example, in the automotive industry or in electrical and precision engineering.

Due to its good resistance to media and wear, Klüber TP 39 N A/B is also particularly suitable for dynamic loads when used in combination with oil lubrication.

Application notes

Klüber TP 39 N A/B consists of:

Component A, (Art. No. 099199) and component B. Klüber TP 39 N A/B component B is used as component B (Art. No. 0099200).

Component B is mixed with component A at a 5 wt. % to 95 wt. % ratio.

Example: 50 g of component B with 950 g of component A.

Prior to mixing the components, stir component A to remove any bottom deposits. Use a slow-moving stirrer (500 to 800 rpm, stir for at least 15 min) or a high-speed jetstream stirrer, e.g. made by Ystral, drive x 40/36, shaft LDT-1, mixing generator Ø 65 mm (approx. 10 000 rpm, stir for 5 min).

Upon stirring, add component B. The mixture should be homogenised either by the above-mentioned slow-moving stirrer for 15 min, or by the high-speed jetstream stirrer for 5 min. If the high-speed stirrer is used, make sure the temperature of the mixture does not significantly exceed 30 °C.

After mixing, pass the mixture through a poly-ethylene filter with approx. 150 µm pore size.

The mixing container should always be covered with a lid.

The mixture of components A and B can be processed for approx. 24 h provided the ambient temperature is not much above 25 °C (pot life).

Any tubes in contact with the mixture must be made of polyethylene or PTFE. The mixture is applied to the component by means of spraying. The recommended layer thickness for tribological loads is 5 to 25 µm (dried coating). For special applications, layers up to 70 µm thickness may be applied.

For application by means of spray systems, we recommend a stirrer to be installed in the mixture container and circulating mixture feed. This helps to prevent the solid lubricants from settling.

Klüber TP 39 N A-B

Two-component PTFE bonded coating for metal components

Please ensure that the relative atmospheric humidity is fairly low (max. 60 %) during application processes (coating and deaeriation).

If atmospheric humidity is too high, water will be absorbed into the wet applied film (product is hygroscopic). This may impair the lubricating film's performance, especially if the coating is applied wet-on-wet.

To clean the spray equipment and dilute the bonded coating, the Klüber solvent and cleaning agent SOLUTIN C 10 (Art. No. 058036) may be used.

Opened containers of both components should be closed again immediately after use.

When subjected to a heat treatment of 100 °C the coated parts are dry to the touch after approx. 6-8 minutes.

Drying / hardening

The coating is hardened at 230 °C object temperature for at least 15 min.

The product will only offer its full performance if hardened completely as described. To obtain a bubble-free coating, especially when its thickness is > 15 µm, the coated component should be allowed to deaerate for 10 to 15 min at a temperature between 80 °C and 120 °C prior to hardening at 230 °C.

Pretreatment

To attain optimum adhesion of the bonded coating, the component surface must be cleaned and degreased. It should also be roughened prior to coating, either by means of sandblasting or application of a phosphate layer. When applied under bonded coatings, phosphate layers help to increase corrosion resistance.

The maximum storage temperature of 25 °C should not be exceeded but for a short time.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	Klüber TP 39 N A/ BKomp. A
Can 950 ml	+
Bucket 17.1 l	+
Bottle 50 ml	-
Can 900 ml	-

Product data	Klüber TP 39 N A/ BKomp. A
Article number	099199
Service temperature, lower limiting value (standard mixture)	-40 °C
Operating temperature, upper limit value (standard mixture)	230 °C
Colour space	black
Colour space, (standard mixture)	black
Texture	liquid
Density, DIN EN ISO 2811, at 20 °C	approx. 1.05 g/cm ³
Density DIN EN ISO 2811, 20°C (standard mixture)	approx. 1.05 g/cm ³
Non-volatile matter, DIN EN ISO 3251, t=1h, T=230°C, recirculating air drying cabinet, dish d~10 cm	approx. 26 % by weight
Mixing ratio of components (standard mixture)	95 : 5



Product data	Klüber TP 39 N A/ BKomp. A
Runout time, DIN EN ISO 2431, with flow cups, 3 mm nozzle	
Runout time, DIN EN ISO 2431, with flow cups, nozzle 6 mm	approx. 53 s
Flash point, DIN EN ISO 1516, -30 °C to 110 °C	approx. 28 °C
Runout time, DIN EN ISO 2431, with flow cups, 6 mm nozzle (standard mixture)	approx. 45 s
Salt spray test, DIN EN ISO 9227, 5% NaCl, temperature 35°C, material steel ST 1405, layer thickness 15 µm, corrosion after	>= 180 h
Salt spray test, DIN EN ISO 9227, linked with DIN EN ISO 7253, 5% NaCl, temperature 35°C, material steel zinc-phosphatized, layer thickness 15 µm, corrosion after	>= 500 h
Friction coefficient, Tannert sliding indicator, room temperature, v _{max} = 0.243 mm/s, F = 50 - 300 N	approx. 0.03
Yield with a tribo-film thickness of 15 micrometer (standard mixture)	approx. 13.5 m ² /l
AC ² T sliding friction test rig, ball/disc, T = 20°C, v = 0.16 m/s, F = 30 N, layer thickness = 15 µm	>= 120 min
AC ² T sliding friction test rig ball/disc, ambient temperature, v = 0.16 m/s, F = 30 N, friction coefficient µ	approx. 0.15
AC ² T sliding friction test rig ball/disc, ambient temperature, v = 0.16 m/s, F = 50 N, friction coefficient µ	approx. 0.1
AC ² T sliding friction test rig, ball/disc, ambient temperature, v = 0.16 m/s, F = 50 N, layer thickness = 15 µm	approx. 10 min
Cross-cut adhesion (test plate), PA-063 based on DIN EN ISO 2409, value	0 Gt
Mandrel bending test, DIN EN ISO 1519, material tinplate, layer thickness 10 - 80 µm, temperature -40 °C, mandrel diameter 2 mm	passed
Media resistance of coatings, based on DIN EN ISO 2812-1, tested at room temperature, layer thickness approx. 15 µm, substrate steel, medium 0.1n hydrochloric acid, result: film resistant, tested up to	1 000 h
Media resistance of coatings, based on DIN EN ISO 2812-1, tested at room temperature, layer thickness approx. 15 µm, substrate steel, medium diester oil, result: film resistant, tested up to	1 000 h
Media resistance of coatings, based on DIN EN ISO 2812-1, tested at room temperature, layer thickness approx. 15 µm, substrate steel, medium soda lye, result: film resistant, tested up to	1 000 h
Media resistance of coatings, based on DIN EN ISO 2812-1, tested at room temperature, layer thickness approx. 15 µm, material steel ST 1303, medium doped mineral oil, result: film resistant, tested up to	1 000 h
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	12 months



Klüber[®]top TP 39 N A-B

Two-component PTFE bonded coating for metal components



Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 80 years.

**Klüber Lubrication München SE & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.**

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München SE & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München SE & Co. KG and if source is indicated and voucher copy is forwarded.